



MATERIAL SPECIFICATION

GRADE G-5

Density, gm/cc	1.90
Lbs per sq ft (1/8 th)	1.23
Tensile Strength, PSI, lengthwise	37,000
Tensile Strength, PSI, crosswise	30,000
Compressive Strength, PSI, flatwise	70,000
Flexural Strength, PSI, lengthwise	65,000
Flexural Strength, PSI, crosswise	50,000
Hardness, Rockwell (M)	120
Dielectric Strength, VPM, perpendicular (1/16 th)	350
(1/8 th)	260
Water Absorption, % 24hrs (1/16)	1.00
(1/8 th)	0.60
(1/2)	0.40
Heat Resistance, degrees F, continuous	280

Grade G-5 is a hi-strength Glass-Melamine laminate with resistance to flame, heat and arcing and tracking. It resists extreme compressive loads and offers amongst the highest Bonding Strengths of all Thermoset laminates.



Tel: (450) 430-3030 • Fax: (450) 430-3031 • Toll Free: 1-888-475-8843
info@synthanetaylor.com • www.synthanetaylor.com

Values are based on typical Test Methods and Conditions and to be used for Engineering and Design Purposes only