



MATERIAL SPECIFICATION

GRADE G-3

Density, lbs/cu in	0.070
Tensile Strength, PSI, lengthwise	53,000
Compressive Strength, PSI, flatwise	55,800
Flexural Strength, PSI, 1/8 th	59,000
Hardness, Rockwell (M)	120
Impact Strength, ft-lb/in	15.0
Dielectric Strength, KV, parallel Cond A	78
Dissipation Factor @ 1Mhz	0.023
Dielectric Constant @ 1Mhz	7.16
Arc Resistance, seconds	180
Water Absorption, % 24 hrs (1/8 th)	0.61
Heat Resistance, degrees C, continuous, mechanical	200C
electrical	140C

Grade G-3 is a glass-phenolic laminate offering excellent Thermal Endurance and with high mechanical strengths and electrical value.

It is UL-recognized to be flame retardant – self extinguishing – UL94V-0.



Tel: (450) 430-3030 • Fax: (450) 430-3031 • Toll Free: 1-888-475-8843

info@synthanetaylor.com • www.synthanetaylor.com

Values are based on typical Test Methods and Conditions and to be used for Engineering and Design Purposes only